

Technical data sheet Version 1

Protective and decorative impregnation AQUA

TY 2316-003-49630959-04

Purpose For protective and decorative finishing of wood, including valuable species of wood inside and outside the premises.

Properties Emphasizes the structure of wood, does not impair its strength and adhesiveness. It has bioprotective, water repellent properties

Composition Water
Styrene acrylic latex
Special antiseptic additives
Transparent pigments

Colors	Colorless	Mahogany
	Frosting	Teak
	Pine	Walnut
	Cowslip	Oak
	Larch	Wenge
	Cherry	Rosewood

Packing Plastic containers weighing 0.9kg, 2.5kg, 10kg.

Technical Specifications

Film appearance after drying	Smooth, no visible inclusions
Viscosity according to VZ-246 viscometer, nozzle diameter 4 mm, sec, no less	30
Mass fraction of non-volatile substances, %, no less	12
Film resistance to static action of water at (20±2)°C, h, no less	24
Frost resistance, cycles	5
Drying time up to degree 3	1
at (20±2) oC, hour, not more	24
Total drying time, hour	1,03-1,1

Storage conditions Store in a tightly closed container, away from heaters and direct sunlight, at a temperature not lower than +5°C. In case of freezing products thaw at room temperature and mix thoroughly until homogeneous mass. After thawing it completely retains its properties.

Guaranteed shelf life In unopened container manufacturer 60 months from the date of manufacture.

Transportation By all means of transport in conditions excluding the influence of atmospheric factors (covered vans, wagons, etc.). Duration of transportation at temperatures below 0°C should not exceed 1 month. Product does not belong to dangerous goods. Code of emergency measures is not required.

Waste management Containers and unused remains of impregnation after drying are disposed of as household waste.

Safety Products are fire and explosion-proof and non-toxic. Use personal protective equipment. When using the product do not smoke, do not drink, do not eat. In case of contact with skin and eyes wash with water. Keep out of reach of children. Avoid contact with water and soil.

All information is correct on the day of publication. Published technical data and instructions are subject to change without notice.