

# Technical data sheet Version 2

# **Bath and Sauna impregnation**

ТУ 2316-003-49630959-04

Purpose	To protect surfaces inside wet areas (sauna, bath).
Properties	Protects against moisture, mold, mildew. Preserves the natural color of wood, increases its service life. Does not have an unpleasant smell. Do not mix with other compositions. It is allowed to introduce up to 3% of tinting pastes.
Composition	Acrylic latex Water Special additives
Packing	Plastic container volume of 1L, 3L, 10L.

### **Technical Specifications**

Appearance	Colorless
Viscosity according to VZ-246 viscometer, nozzle diameter 4 mm, sec, no less	30
Mass fraction of non-volatile substances, %, no less	20
Frost resistance, cycles	5
Drying time up to degree 3	1
at (20±2) oC, hour, not more	72
Total drying time, hour	10-12 л на 1м²

## Storage conditions Store

Store in a tightly closed container, away from heaters and direct sunlight, at a temperature not lower than +5oC. In case of freezing products thaw at room temperature and mix thoroughly until homogeneous mass. After thawing it completely retains its properties.

#### **Guaranteed shelf life**

In unopened container manufacturer 60 months from the date of manufacture.

### **Transporting**

By all means of transport in conditions excluding the influence of atmospheric factors (covered vans, wagons, etc.). Duration of transportation at temperatures below 0°C should not exceed 1 month. Product does not belong to dangerous goods. Code of emergency measures is not required

Waste management	Containers and unused remains of impregnation after drying are disposed of as household waste.
Safety	Products are fire and explosion-proof and non-toxic. Use personal protective equipment for hands and respiratory system. When using the product do not smoke, do not drink, do not eat. In case of contact with skin and eyes wash with water. Keep out of reach of children. Avoid contact with water and soil.

All information is correct on the day of publication. Published technical data and instructions are subject to The published technical data and instructions are subject to change without notice.